

260°C ELECTRICALLY RESISTANT EPOXY

Cures at Room Temp. to Bond, Pot, Seal and Protect

260°C - DURALCO™ 4525 & 4525IP

Easy to use. Just mix and apply.

No volatiles. No solvents. No out-gassing.

Duralco™ 4525 cures at room temp. (or in 5 minutes at 120°C) to provide high bond strength, high temp. stability, low shrinkage, excellent chemical, electrical and radiation resistance and low moisture absorption.

It maintains its high electrical resistance over long periods of time and has the lowest moisture absorption available when compared to 23 commercially available epoxies. (This application has been approved by UL).

Duralco™ 4525 is ideal for high performance bonding, potting, sealing, repairs, castings and jigs. Forms protective coatings. Commonly found in electronics, appliances, instrumentation, motors, equipment, etc.

Users Report:

High Resistance Even in High Humidity

Used to seal thermocouples, electric heaters and critical electronic components for use in high humidity environments. Tests show less than 10% of the moisture transmission of silicones or competitive epoxies.

Proven in Instrumentation Applications

Used for fabrication of end seals and installation of thermocouples, pressure, strain gauges and flow measuring instruments.

Excellent Corrosion Resistance

Used to repair glass lined tanks for use in 36% Hydrochloric, 29% Phosphoric, 65% Sulfuric and 70% Nitric Acids, 25% Caustic, 30% Chrome Oxide solutions. Competitive epoxies disintegrated in less than 24 hours.

Bonds Carbon to Steel and Remains in use for 5 years

Used to bond carbon blocks to steel for bearings in a rotating kiln at 150°C. Bonds brake pads.

Fast Cures

Independent tests have shown 95% cure in 15 minutes at 95°C and 100% cure in 5 minutes at 120°C, enabling high speed production applications.

Availability:

Cat. No.	Description	Temp.
Duralco 4525-1.....	Pint Kit.....	260°C
Duralco 4525-2.....	Gallon Kit.....	260°C
Duralco 4525IP-1.....	Pint Kit.....	260°C
Duralco 4525IP-2.....	Gallon Kit.....	260°C

Pre-Measured Kits

Each Unit Contains: 1 jar of resin, 1 syringe of hardener and 1


EE4525-10.....	Epoxy-Eez 10gm units/box
EE4525-25.....	Epoxy-Eez 25gm units/box
EE4525IP-10.....	Epoxy-Eez 10gm units/box
EE4525IP-25.....	Epoxy-Eez 25gm units/box

Also Available in Epoxy-Eez Twin Pack Cartridges


Quantity Prices & Custom Formulations
Available on Request



**4525 Bonds a 316 S.S. Shaft to a Ceramic Piston
Repairing a High Temperature Acid Pump**



**Duralco™ 4525 Insulates, Seals and
Moisture-Proofs a Hi- Temp Instrument**



Duralco 4525™ Bonds a Hi-Temp. Brake Assembly

Duralco™	4525	4525IP
Maximum Temperature	260°C	260°C
Components - Color	2-Black	2-Black
Mixed Density (gms/cc)	1.7	1.9
Mixed Viscosity (cps)	12,400	24,000
Hardness (Shore D)	90	90
Tensile Strength (psi)	10,000	10,000
Thermal Cond.(BTU-in/Hr. Ft ² °F)	13	13
Thermal Expansion (10 ⁻⁵ /°C)	3.3	3.1
Dielectric Strength (volts/mil.)	450	425
Volume Resistivity (ohm-cm)	10 ¹⁵	10 ¹⁵
Heat Distortion (°C)	210	213
Elongation (%)	2	2
Thermal Stability (% 1000 hr @ 200°C)	0.05	0.05
Shrinkage (% max.)	0.2	0.2
Moisture Absorption (% 30 days)	0.1	0.2
Mix Ratio (R/H)	100:8	100:8-12
Cure (Hr. @ R.T.)	16-24*	16-24*
Optimum properties post cure hrs. @ 121°C	5	1
and hrs. @ 176°C	1	1

* Cures can be accelerated with mild heat.